

Océ Specifications



Océ Cold PP/PET Embossed Lamination Film 150µm

Non glare, embossed laminate for display applications

Océ Imaging
Supplies
Product Info

FIN981

Display Graphics
Version 2

Product description PP/PET film with a textured lustre finish, coated with a pressure sensitive water-based acrylic adhesive and backed with a silicon glassine release liner.

Physical Properties	Thickness film + adhesive	150 µm ± 10%	ISO 534
	Quick tack on glass (N/25mm)	13	FTM 9
Peel 180° on glass (N/25mm)	after 20 minutes	10	FTM1 (ASTM D 903-49)
	after 24 hours	11	FTM1 (ASTM D 903-49)
Dimensional Stability	MD / CD	0.6 / 0.3%	FTM 14

Features
 Unique finish that virtually eliminates glare
 Dimensionally stable laminate for indoor use
 Ideal for use with Printable Light Block Films
 Good bond to inkjet matt and glossy media
 Scratch resistant

Available sizes	width (mm)	length (m)	article number
	914	50	973 10 381

Storage conditions Temperature 15 – 25 °C ; Relative Humidity 10 – 80%
 It is advised that the rolls are stored on end or suspended from the core (hanging in plugs)

Shelf life 2 years when stored at 15 to 25 °C and approx. 50%RH

Environment, Health & Safety No Material Safety Data Sheet required

Main Applications Laminate for Roll-Up systems and Pop-Up Display walls
 Flexible, rigid and mounted posters



Océ Cold PP/PET Embossed Lamination Film 150µm

Non glare, embossed laminate for display applications

Processing Information

User Tips

Adhesive is on the outer side of the roll

Film was designed for cold, pressure sensitive lamination.

Good drying of the inks of the print is required to obtain proper adhesion

Typical settings for lamination: 15 - 40°C / 30 psi / 5 m /min dependent on substrate

The use of limited heat (up to 40°C) will give very good results

Film can be applied to non-mounted and already mounted images

This product is typically meant for use at front side

Allow min 24 hours of time after lamination before rolling for transport

Roll with laminate to the outside

Océ-Technologies B.V.

P.O. Box 101

5900 MA Venlo, The Netherlands

Tel (31) (77) 3592222

www.oce.com

Page 2 of 2

